

ALL PURPOSE 3006[™] ADVANCED FORMULA STIN FIL Siliconized Acrylic Latex Caulk

White Lightning[®] 3006[™] Advanced Formula provides a smooth application that can be painted in 30 minutes! It is ideal for filling joints and openings around doors, windows, baseboards, trim, siding and vents. For use on: wood, drywall, metal, glass, masonry and most plastics.

- Smooth Application
- Excellent Adhesion to Most Surfaces
- Cured Sealant is Mold and Mildew Resistant
- Paintable in 30 minutes









Exceeds ASTM C-834







ALL PURPOSE 3006™ ADVANCED FORMULA

Product Description:

White Lightning[®] 3006[™] Advanced Formula provides a smooth application that can be painted in 30 minutes! It is ideal for filling joints and openings around doors, windows, baseboards, trim, siding and vents. For use on: wood, drywall, metal, glass, masonry and most plastics.

Physical Properties:

Type: 100% Pure Acrylic With Silicone **Colors:** White Shelf Life: 24 Months Flash Point: n/a (water based) Flammability: n/a (water based) Full Cure Time: 5 to 7 days at 75° F Tack Free Time: 10 Minutes Application Temperature: above 40° F Service Temperature: -30° F to 180° F **Vehicle:** Premium siliconized acrylic polymer Solids by Weight: $83.5 \pm 1\%$ Weight/Gallon: 13.2 ± 0.2 lb **Painting:** Paintable **Primers:** Not required Mildew Resistance: Cured caulk resists mildew growth Water Resistance: Good Odor: Low Shrinkage: Low/Moderate

Performance Data:

Joint Size: 1/8" x 1/8" to 1/2" x 1/2" Freeze-Thaw Stability: Stable through 5 Cycles Shelf Life: 24 Months Clean Up: Clean tools and excess sealant with soap and water or a damp cloth while still wet. Flexibility: Very Good Linear Coverage 10oz cartridge 24ft at 1/4" wide by 1/4" deep bead; 5.5oz squeeze tube 12ft at 1/4" wide by 1/4" deep bead Painting: (Temperature and Humidity Dependent) Can be painted with latex or oil based paint after 30 minutes dry time at 75°F and 50% relative humidity. Allow extra dry time during periods of high humidity and/or cool temperatures. ASTM: Exceeds ASTM C-834

Application:

1. Remove all existing caulk

2. Clean thoroughly to remove all loose material, grease, dirt, oil, wax, loose paint, dust and soap film.

3. Remove mold/mildew with bleach (4:1 mix, water to bleach), and detergent that does not contain ammonia. Rinse surfaces and allow to dry.

• 10oz cartridge

- Cut cartridge tip 45° angle.
- Load cartridge into caulk gun.
- Squeeze trigger to start flow of caulk and work caulk into joint.
- Smooth caulk with proper tool.

5.5oz cartridge

- Remove cap, cut tube tip 45° angle.
- · Squeeze tube to start flow of caulk and work caulk into joint.
- Smooth caulk with proper tool.

Clean Up:

Water, promptly clean tools and excess sealant with water or a damp cloth while still wet.

Cautions:

See SDS

Limitations:

For best results, apply at temperatures above 40° F and allow 24 hours to cure before exposing to moisture. Do not apply to frozen or frost covered surfaces. Not for use below grade, on aquariums or for marine use below the water line

LIMITED WARRANTY:

For 45 years from date of purchase, if when applied according to label directions within one year from date of purchase, if this product fails to perform in accordance with the specifications set forth on this label, as your sole remedy, upon proof of purchase, we will replace the product at no cost or refund the original purchase price. Labor or costs associated with labor not included. Applies to single family house only. This warranty is made to the original residential consumer purchaser and is not transferable. THIS WARRANTY IS IN LIEU OF ALL OTHER WARRANTIES, EXPRESS OR IM-PLIED, INCLUDING MERCHANTABILITY, WHICH ARE ALL DISCLAIMED AND/ OR LIMITED IN DURATION TO THE EXTENT PERMITTED BY LAW. WE SHALL NOT BE LIABLE FOR INDIRECT, SPECIAL, INCIDENTAL OR CONSEQUENTIAL DAMAGES (INCLUDING LOST PROFITS) FROM ANY CAUSE WHATSOEVER.

For more information please call or write:

White Lightning[®] Products | 101 Prospect Ave. NW | Cleveland, OH 44115 1-800-241-5295 Option 1 Customer Service | 1-800-241-5295 Option 2 Technical Service www.wicaulk.com